

PRODUCT SPECIFICATION SHEET

BELZONA 1521

FN10037



GENERAL INFORMATION

Product Description:

A two component spray applied high temperature coating system designed to operate under continuous immersion at operating temperatures up to 302°F (150°C). Suitable for steaming out up to 410°F (210°C). Exhibits excellent corrosion resistance at elevated temperatures. Resistant to a broad range of aqueous solutions, hydrocarbons and process chemicals. (Refer to Belzona TKL for specific recommendations). Applied by heated airless spray. For use in Original Equipment Manufacture or repair situations.

Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- Condensate return tanks
- Autoclaves
- Regenerators
- Evaporators
- Scrubber units
- Stripper towers
- Oil/gas and oil/water separators
- Distillation units

APPLICATION INFORMATION

Working Life

Will vary according to temperature. At 68°F (20°C) the usable life of a 10 litre unit of mixed material is 40 minutes.

Coverage Rate

The **Belzona 1521** shall be applied to achieve a minimum thickness of 20 mils (500 microns). The theoretical coverage rate at 20 mils (500 microns) is 21.5 sq.ft. (2 m²)/litre. Refer to the Instructions For Use for practical coverage rate guidelines.

Cure Time

Allow the applied material to solidify for the times shown in the Belzona IFU before subjecting it to the conditions indicated

** In certain instances it may be advantageous to post cure material prior to putting into service where chemical contact is involved. Refer to Belzona for specific recommendations.*

Base Component

Appearance Paste
Color Grey
Density 1.95 - 2.05 g/cm³

Solidifier Component

Appearance Liquid
Color Clear
Density 0.93 - 0.95 g/cm³

Mixed Properties

Mixing Ratio by Weight (Base : Solidifier) 20 : 1
Mixing Ratio by Volume (Base : Solidifier) 9.5 : 1
Mixed Form Liquid
Sag resistance nil at 40 mil (1 mm)
Mixed Density 1.8 - 1.9 g/cm³

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 1521

FN10037



ABRASION

Taber

The Taber abrasion resistance determined in accordance with ASTM D4060 with 1 kg load, H10 Wheels (Wet) is typically:

770 mm³ loss/1000 cycles 212°F(100°C) post cure

ADHESION

Tensile Shear

When tested in accordance with ASTM D1002, using degreased strips, grit blasted to a 3-4 mil profile, typical values will be:

	Post cure/ Test temperature	Adhesion
Mild steel	68°F (20°C)	2180 psi (15.03 MPa)
	140°F (60°C)	1650 psi (11.38 MPa)
	212°F (100°C)	1410 psi (9.72 MPa)

Pull Off Adhesion

When tested in accordance with ASTM D 4541/ ISO 4624, the pull off strength from grit blasted steel will be typically:

5260 psi (36.27 MPa)	Cure temperature
4370 psi (30.13 MPa)	68°F (20°C)
	212°F (100°C)

CHEMICAL RESISTANCE

Once fully cured, the material will demonstrate excellent resistance to a wide range of chemicals.

* For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.

COMPRESSIVE PROPERTIES

When determined in accordance with ASTM D695, typical values will be:

Compressive Strength	Post cure/Test temperature
13,520 psi (93.22 MPa)	68°F (20°C)
10,840 psi (74.74 MPa)	212°F (100°C)

EXPLOSIVE DECOMPRESSION

When tested to NACE TM 0185, using a seawater/hydrocarbon test fluid, the coating will exhibit no blistering after a 21 day immersion period at 248°F (120°C) and 70 bar pressure followed by decompression over 15 minutes.

FLEXURAL PROPERTIES

When determined in accordance with ASTM D790, typical values will be:

Flexural Strength	Post cure/Test temperature
6170 psi (42.54 MPa)	68°F (20°C)
3910 psi (26.96 MPa)	212°F (100°C)

HARDNESS

Shore D

When determined in accordance with ASTM D2240, typical values will be:

86	Cure temperature
86	68°F (20°C)
	212°F (100°C)

Barcol

When determined in accordance with ASTM D2583, will typically be:

92	68°F (20°C)
95	212°F (100°C)
96	302°F (150°C)

Koenig Pendulum

When tested to ISO 1522 the Koenig damping time will typically be:
126 seconds 68°F (20°C)

HEAT RESISTANCE

Heat Distortion Temperature (HDT)

Tested to ASTM D648 (264 psi fiber stress), typical values obtained will be:

131°F (55°C)	Cure temperature
330°F (166°C)	68°F (20°C)
493°F (256°C)	212°F (100°C)
	356°F (180°C)

Atlas Cell

When tested in accordance with NACE TM 0174 the coating will exhibit no rusting (ASTM D610 rating 10) or blistering (ASTM D714 rating 10) after 6 months immersion in de-ionized water at 203°F (95°C).

Steam-out Resistance

Once fully cured the coating will exhibit no blistering, cracking or delamination after 96 hours exposure to pressurised steam at 410°F (210°C).

Wet Heat Resistance

The coating will resist water and hydrocarbon mixtures at temperatures up to 302°F (150°C). Note: the material is not recommended for dry applications at elevated temperatures.

Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO11357 is typically 428°F (220°C).

PRODUCT SPECIFICATION SHEET

BELZONA 1521

FN10037



THERMAL PROPERTIES

Low Temperature Thermal Shock

Coated steel panels will exhibit no blistering, cracking or delamination after multiple cycles of rapid cooling from 212°F (100°C) to -76°F (-60°C).

Thermal Cycling

When tested in accordance with section 9 of NACE TM0304, the coating passed after 252 cycles between +140°F and -22°F (+60°C and -30°C).

THICK FILM CRACKING

Thick Film Cracking

When tested in accordance with Section 12 of NACE TM0104, the coating at three times recommended thickness, exhibited no cracking after 12 weeks immersion in seawater at 104°F (40°C).

SHELF LIFE

Separate Base and Solidifier components will have a minimum shelf life of 3 years when stored in their original unopened containers between 32°F (0°C) and 86°F (30°C).

WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 1521 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000 N.W. 88th Court,
Miami, Florida, USA, 33172

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2015 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

