

PRODUCT SPECIFICATION SHEET

BELZONA 4181

FN10079



GENERAL INFORMATION

Product Description:

A heat or acid resistant trowelable system for repair and protection of concrete, stone and other rigid substrates subject to impact and abrasion. Designed for resistance to Inorganic acids, **Belzona 4181** uses a complex acid catalysable hybrid resin system incorporating closely packed acid resistant fillers. The product is supplied as a 3 component system, Base, Solidifier and Aggregate, that when combined, forms a trowelable consistency to rebuild damaged surfaces or to provide an impact and abrasion resistant surface.

Application Areas:

Ideally suited for horizontal surfaces, the system may be applied on vertical surfaces up to ¼" (6mm) thickness. Having outstanding adhesion, strength, hardness and acid resistance, **Belzona 4181** is ideally suited for :-

- Chemical drains and channels
- Gulleys
- Bunds
- Chemical transfer and holding areas
- Tank pads
- Pump bases
- Ovens

APPLICATION INFORMATION

Working Life

Will vary according to temperature. At 77°F (25°C), use all mixed material within 30 minutes.

Coverage Rate

Each 15 kg unit applied at the minimum recommended film thickness of ¼ inch will cover approximately 10.67 sq.ft. (1.05 m² at a thickness of 6mm).

Cure Time

Will be reduced for thicker sections and extended for thinner applications. Allow to solidify for the times shown in the IFU before subjecting it to the conditions indicated.

Volume Capacity

384 cu.ins. (6300 cm³) per 15 kg unit.

Base Component

Appearance Clear Liquid
Colour Light amber
Viscosity 40 - 50 poise at 77°F (25°C)
Density 1.17 - 1.19 g/cm³

Solidifier Component

Appearance Clear Liquid
Color Amber
Viscosity 3 - 6 cPs at 77°F (25°C)
Density 1.05 - 1.07 g/cm³

Aggregate Component

Appearance Pre-wetted, fine granular powder
Color Red
Density 2.5 - 2.7 g/cm³

Mixing Ratio

For mixing small quantities the mixing ratio by weight of the component is:-
(Base : Solidifier : Aggregate) 100 : 30 : 1000

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 4181

FN10079



ABRASION

Taber

When tested in accordance with ASTM D4060 using H10 wheels wet, 1 kg load, typical loss per 1,000 cycles is 395 mm³

ADHESION

Tensile Shear

The tensile shear adhesion to steel of the polymeric binder, when tested in accordance with ASTM D1002 is typically 2,400 psi (16.5 MPa).

Elcometer

Dry concrete 600 psi (4.14 MPa)*

* Cohesive failure of substrate

CHEMICAL RESISTANCE

The material offers good resistance to a broad range of chemicals, particularly inorganic acids.

* For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.

COMPRESSIVE PROPERTIES

Compressive Strength

When tested in accordance with ASTM D695 the compressive strength is typically 9,150 psi (63.1 MPa).

FLEXURAL PROPERTIES

Flexural Strength

The flexural strength of the material (binder/ aggregate matrix), when tested to ASTM D790 is typically:

6,444 psi (44.4 MPa).

HEAT RESISTANCE

Heat Distortion Temperature (HDT)

The heat distortion temperature when tested to ASTM D648 is typically:

Ambient cure	129°F (54°C).
Post cure @ 100°C	365°F (186°C)
Post cure @ 150°C	420°F (216°C)

Heat Resistance

For many typical applications involving impact or abrasion, the product is suitable up to 300°F (150°C). The material is not recommended for chemical immersion at elevated temperatures.

SHELF LIFE

All components will have a shelf life of at least 5 years when stored between 32°F (0°C) and 86°F (30°C).

PRODUCT SPECIFICATION SHEET

BELZONA 4181

FN10079



WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 4181 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000 N.W. 88th Court,
Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2015 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

